

# Far East American Lamination Grade Birch



Lamination grade uses only the best available A grade poplar core veneer. The core veneer is without dead knots, without patches and is uniform in color.

All core veneers are 100% machine composed.

The core is precisely calibrated to ensure there are no low spots.

All panels are constructed for use with a CNC router.

They are suitable for lamination with a variety of laminates such as high pressure laminate (HPL) and 30 gram paper.

Lamination panels are all produced at one factory to ensure consistent quality.

All panels are inspected by FEA quality control personnel.

THICKNESS	TYPE	WEIGHT	PANEL CONSTRUCTION
9 mm	Poplar Core	32 lbs.	7
	Combi Core	33.5 lbs.	
12 mm	Poplar Core	40.3 lbs.	9
	Combi Core	43 lbs.	
18 mm	Poplar Core	60.6 lbs.	13
	Combi Core	64.4 lbs.	
SPECIFICATIONS			
dimension:	4' x 8'; available in 48.5" x 96.6"		
face/back:	available in natural and white birch		
grade:	available in C-D, D-D and D-E		
glue:	available in E-I and CARB 2		
tolerance:	minus .5 mm/plus .2 mm		
moisture content:	8 - 12%		

